

KOERDYM™ I

Injection Molded NdFeB

Grade	(BH) max		Br		HcJ		HcB	
	kJ/m ³	MGOe	mT	G	kA/m	Oe	kA/m	Oe
Koerdym I 32PA	32	4.0	450	4500	1000	12566	300	3770
Koerdym I 35PA	35	4.4	480	4800	650	8168	300	3770
Koerdym I 38PA	38	4.8	490	4900	1000	12566	320	4021
Koerdym I 39PA	39	4.9	480	4800	590	7414	310	3896
Koerdym I 42PA	42	5.3	520	5200	650	8168	320	4021
Koerdym I 43PA	43	5.4	520	5200	760	9550	330	4147
Koerdym I 47PA	47	5.9	550	5500	550	6912	330	4147

*All values are typical