

KOEROX™ I

Injection Molded Ferrite

| Table of Properties Grade | (BH) max | | Br | | HcJ | | HcB | |
|------------------------------|-------------------|------|-----|------|------|------|------|------|
| | kJ/m ³ | MGOe | mT | G | kA/m | Oe | kA/m | Oe |
| Koerox I 1/20 PA | 1.7 | 0.21 | 103 | 1030 | 220 | 2765 | 70 | 880 |
| Koerox I 2/20 PA | 2.7 | 0.34 | 128 | 1280 | 220 | 2765 | 86 | 1081 |
| Koerox I 5/22 PA | 5.2 | 0.65 | 170 | 1700 | 220 | 2765 | 120 | 1508 |
| Koerox I 6/22 PA | 6.7 | 0.84 | 190 | 1900 | 220 | 2765 | 131 | 1646 |
| Koerox I 9/22 PA | 8.9 | 1.12 | 219 | 2190 | 220 | 2765 | 151 | 1898 |
| Koerox I 9/30 PA | 8.9 | 1.12 | 220 | 2200 | 300 | 3770 | 151 | 1898 |
| Koerox I 10/22 PA | 10.3 | 1.29 | 236 | 2360 | 220 | 2765 | 157 | 1973 |
| Koerox I 12/23 PA | 11.5 | 1.45 | 250 | 2500 | 230 | 2890 | 161 | 2023 |
| Koerox I 13/24 PA | 13.0 | 1.63 | 265 | 2650 | 235 | 2953 | 173 | 2174 |
| Koerox I 14/24 PA | 14.3 | 1.80 | 276 | 2760 | 230 | 2890 | 175 | 2199 |
| Koerox I 8/20 PS | 7.5 | 0.94 | 200 | 2000 | 195 | 2450 | 134 | 1684 |
| Koerox I 8/29 PS | 7.4 | 0.93 | 205 | 2050 | 300 | 3770 | 136 | 1709 |
| Koerox I 9/18 PS | 10.2 | 1.28 | 235 | 2350 | 180 | 2262 | 147 | 1847 |
| Koerox I 11/18 PS | 11.7 | 1.47 | 250 | 2500 | 167 | 2099 | 138 | 1734 |

*All values are typical